

Certificate of Test

QUOTE No.: NE8282

REPORT No.: FNE12493

AS/NZS 1530.3:1999 SIMULTANEOUS DETERMINATION OF IGNITABILITY, FLAME PROPAGATION, HEAT RELEASE AND SMOKE RELEASE

TRADE NAME: Blue Mountain Co Gutter Mesh 4mm Aluminium Ultra

SPONSOR: Rain Harvesting Pty Ltd
12 Mayneview Street
MILTON QLD 4064
AUSTRALIA

DESCRIPTION OF SAMPLE:

The sponsor described the tested specimen as a coated expanded aluminium mesh with aperture size of 4.4-mm by 3.6-mm. The mesh was powder coated with polyethylene on both sides. The specimen is comprised of one 150-mm by 600-mm and one 450-mm by 600-mm pieces juxtaposed together to form the 450-mm by 600 mm dimensions required for testing.

Nominal thickness of aluminium: 0.7 mm
Nominal thickness of coating: 0.04 µm to 0.06 µm
Nominal total thickness: 0.073 mm to 0.075 mm
Nominal mass: 0.7 kg/m²
Colour: grey (as sighted by laboratory)

TEST PROCEDURE: Six (6) specimens were tested in accordance with AS/NZS 1530, Method for fire tests on building components and structures, Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release, 1999. For each test, each sample clamped to the specimen holder in four places.

RESULTS: The following means and standard errors were obtained:

Parameter	Mean	Standard Error
Ignition Time (min)	n/a	n/a
Flame Spread Time (s)	n/a	n/a
Heat Release Integral (kJ/m ²)	n/a	n/a
Smoke Release (log ₁₀ D)	-2.451	0.085

For regulatory purposes these figures correspond to the following indices:

Ignitability Index (0-20) 0	Spread of Flame Index (0-10) 0	Heat Evolved Index (0-10) 0	Smoke Developed Index (0-10) 0 - 1
-----------------------------------	--------------------------------------	-----------------------------------	--

The results only apply to the specimen mounted as described in this report. The results of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

DATE OF TEST: 14 November 2019

Issued on the 4th day of December 2019 without alterations or additions.



Shaw Tran
Testing Officer



Brett Roddy
Group Leader, Fire Testing and Assessments

Copyright CSIRO 2019 ©. Copying or alteration of this report without written authorisation from CSIRO is forbidden.



NATA Accredited Laboratory
Number: 165
Corporate Site No 3625

Accredited for compliance with ISO/IEC 17025 – Testing.

CSIRO INFRASTRUCTURE TECHNOLOGIES

14 Julius Avenue, Riverside Corporate Park, North Ryde NSW 2113 AUSTRALIA
Telephone: 61 2 9490 5444 Facsimile: 61 2 9490 5555 www.csiro.au

